

Product Texts

BERGAMID B70/80G25TM-Z, PA6 reinforced
25% glass fibre
high impact modified, very good impact strength

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	4900 / 7100	MPa	ISO 527
Stress at break	100 / 145	MPa	ISO 527
Strain at break	7 / 4	%	ISO 527
Charpy impact strength, +23°C	105 / 90	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	- / 80	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	30 / 18	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	- / 10	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	223 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	200 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	210 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	28 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	69 / *	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	6.8 / 3.8	-	IEC 62631-2-1
Dissipation factor, 1MHz	2200 / 230	E-4	IEC 62631-2-1
Volume resistivity	1E10 / 1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
Comparative tracking index	500 / -	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	6 / *	%	Sim. to ISO 62
Humidity absorption	1.9 / *	%	Sim. to ISO 62
Density	- / 1270	kg/m ³	ISO 1183

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	150 / *	cm ³ /g	ISO 307, 1157, 1628

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	270	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Delivery form

Pellets

Other text information

Injection Molding

PREPROCESSING

Max. Water Content 0,1%

Pre-Drying: 80°C 4 Hours

PROCESSING

Melt Temperature 270-290°C

Mould Temperature 80-90°C