

N6125G-NAD

PA6-GF25

Pontex Polyblend Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.25	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	127	MPa	ASTM D 638
Flexural Modulus	6671	MPa	ASTM D 790
Flexural Strength	196	MPa	ASTM D 790

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	200	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1300	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

Asia Pacific