

**4TECH 9CD12130 S-D**

PA6-GF30

4Plas

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>4500</b>	MPa	ISO 527
Stress at break	<b>40</b>	MPa	ISO 527
Izod notched impact strength, +23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 180/1A

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>162</b>	°C	ISO 11357-1/-3
Burning behav. at 1.5 mm nom. thickn. Thickness tested	<b>HB</b> <b>1.6</b>	class mm	IEC 60695-11-10 -
Burning behav. at thickness h Thickness tested	<b>HB</b> <b>0.8</b>	class mm	IEC 60695-11-10 -

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Volume resistivity	<b>1E7</b>	Ohm*m	IEC 62631-3-1
Surface resistivity	<b>1E9</b>	Ohm	IEC 62631-3-2

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1180</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Regional Availability**

Europe