

**AKROMID® B3 GF 30 S1 black (2091)**

PA6-GF30

Akro-Plastic GmbH

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	7500 / 4200	MPa	ISO 527
Stress at break	125 / 70	MPa	ISO 527
Strain at break	6 / 13	%	ISO 527
Flexural modulus, 23°C	6600 / -	MPa	ISO 178
Charpy impact strength, +23°C	110 / 135	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	35 / 45	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	25 / 22	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	200 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E11 / 1E8	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2

Other properties	dry / cond	Unit	Test Standard
Density	1280 / -	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	270	°C	-
Mold temperature	80	°C	-
Injection pressure	75	MPa	-

**Characteristics****Processing**

Injection Molding

**Applications**

Automotive

**Delivery form**

Black

**Regional Availability**

Europe, Asia Pacific

**Special Characteristics**

High impact or impact modified