

**Product Texts**

30% Glass Reinforced

ISO 1043 PA6-GF30

[Akulon® - the all-purpose polyamide](#)[Find the right plastic for your product in our Plastics Finder](#)

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	40 / *	cm <sup>3</sup> /10min	ISO 1133
Temperature	275 / *	°C	-
Load	5 / *	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Density of melt	1150	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	0.27	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	2110	J/(kg K)	-
<sup>[C]</sup> Eff. thermal diffusivity	1.12E-7	m <sup>2</sup> /s	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	9700 / 6000	MPa	ISO 527
<sup>[C]</sup> Stress at break	185 / 110	MPa	ISO 527
<sup>[C]</sup> Strain at break	3.8 / 7	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	95 / 110	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	75 / 75	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	14 / 25	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	11 / 11	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Shore D hardness	85 / *	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	207 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	220 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	216 / *	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	70 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	3.0 / *	mm	-
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning rate, FMVSS, Thickness 1 mm	45	mm/min	ISO 3795 (FMVSS 302)

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	3.5 / 20	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	3.3 / 5	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	50 / 3000	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	150 / 1200	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	1E13 / 1E11	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	* / 1E14	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	30 / 25	kV/mm	IEC 60243-1

[C] Comparative tracking index \* / 600 - IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
[C] Water absorption	6.3 / *	%	Sim. to ISO 62
[C] Humidity absorption	1.9 / *	%	Sim. to ISO 62
[C] Density	1350 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding

### Regional Availability

Europe

### Delivery form

Pellets

## Other text information

### Injection molding

[Injection Molding Recommendations](#)

[Steel recommendations for molds screws and barrels](#)

[Trouble shooting guideline for injection molding](#)