

**Product Texts**

This material displays high mechanical and electrical properties; resilient to hydrocarbons (kerosene, gasoline, benzene etc.), mineral and synthetic oils, strong and weak alkali, weak acids.

Available in black color.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	160	MPa	ISO 527
Strain at break	4.9	%	ISO 527
Charpy impact strength, +23°C	65	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	13	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	218	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	204	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	217	°C	ISO 75-1/-2

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E11	Ohm*m	IEC 62631-3-1
Electric strength	21	kV/mm	IEC 60243-1

Other properties	Value	Unit	Test Standard
Density	1360	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	260	°C	-
Mold temperature	80	°C	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Black

**Features**

Thermal Stability

**Chemical Resistance**

Acid Resistance, Alkali Resistance, Oil Resistance

**Applications**

Aircraft and Aerospace, Automotive, Electrical and Electronical

**Regional Availability**

Europe