

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	8500 / 5500	MPa	ISO 527
Stress at break	130 / 110	MPa	ISO 527
Strain at break	3.5 / 5.5	%	ISO 527
Flexural strength	220 / 190	MPa	ISO 178
Charpy impact strength, +23°C	85 / 100	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	75 / 80	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	18 / 30	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	190 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	205 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	23 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	63 / *	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 1MHz	3.7 / 6.7	-	IEC 62631-2-1
Dissipation factor, 1MHz	230 / 2200	E-4	IEC 62631-2-1
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
Comparative tracking index	500 / -	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	5.9 / *	%	Sim. to ISO 62
Humidity absorption	1.9 / *	%	Sim. to ISO 62
Density	1330 / -	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-
Melt temperature	270 - 290	°C	-
Mold temperature	80 - 90	°C	-

## Characteristics

### Processing

Injection Molding

### Special Characteristics

High impact or impact modified

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa