

**DOMAMID 6LVG30H2 BK**

PA6-GF30

DOMO Engineering Plastics

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1 / *	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	9500 / 6800	MPa	ISO 527
Yield stress	175 / 115	MPa	ISO 527
Stress at break	175 / 115	MPa	ISO 527
Strain at break	3 / 3	%	ISO 527
Flexural modulus, 23°C	7800 / 4800	MPa	ISO 178
Charpy impact strength, +23°C	70 / 65	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	10 / 18	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
<b>Other properties</b>			
Density	1360 / -	kg/m <sup>3</sup>	ISO 1183
<b>Material specific properties</b>			
<b>ISO Data</b>			
Viscosity number	130 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	250 - 290	°C	-
Mold temperature	80 - 100	°C	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Heat stabilized or stable to heat

**Delivery form**

Black

**Regional Availability**

North America, Europe, Asia Pacific