

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	10000	MPa	ISO 527
Stress at break	110	MPa	ISO 527
Strain at break	2.5	%	ISO 527
Flexural modulus, 23°C	9000	MPa	ISO 178
Charpy impact strength, +23°C	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	35	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	221	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	210	°C	ISO 75-1/-2
Vicat softening temperature, B	205	°C	ISO 306
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Comparative tracking index	325	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1430	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	240 - 270	°C	-
Mold temperature	80 - 100	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Flame retardant, Halogen-free, Phosphorus-free