

EPSYLON VT1103 black

PA6-GF30

Omikron

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	5800	MPa	ISO 178
Izod notched impact strength, +23°C	10	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	205	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	-

Other properties	Value	Unit	Test Standard
Density	1340	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Delivery form

Black