

FORMPOLY N6GF30FR

PA6-GF30

Formulated Polymers Limited

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0017	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	160	MPa	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	9000	MPa	ASTM D 790
Flexural Strength	240	MPa	ASTM D 790
Izod Impact notched, 1/8 in	88.3	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 66 psi	200	°C	ASTM D 648
DTUL @ 264 psi	190	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1E14	Ohm	ASTM D 257
Volume Resistivity	1E15	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1600	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets

Special Characteristics

Flame retardant

Features

Low Odor

Chemical Resistance

Environmental Stress Crack Resistance

Applications

Electrical and Electronical

Regional Availability

Asia Pacific