

Fiberfil® FV-30

PA6-GF30

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	150	MPa	ASTM D 638
Flexural Strength	255	MPa	ASTM D 790
Izod Impact notched, 1/8 in	130	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	208	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1370	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets

Regional Availability

North America

Special Characteristics

Heat stabilized or stable to heat