

Product Texts

Product-nomenclature: ISO 16396-PA6,GF30,M1HR,S14-100N

Product Attributes

Improved heat resistance

Markets

Automotive

Air intake systems, Hydraulic systems, Interior

Electricals & Electronics

Electrical appliances, Electrical equipment

Industry & Consumer goods

Housewares, Mechanical Engineering, Power transmission, Sports & Leisure, Tools & Accessories

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.1 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577
^[C] Density of melt	1200	kg/m ³	-
^[C] Thermal conductivity of melt	0.26	W/(m K)	-
^[C] Spec. heat capacity of melt	2200	J/(kg K)	-
^[C] Eff. thermal diffusivity	9.85E-8	m ² /s	-
^[C] Ejection temperature	200	°C	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	10000 / 6500	MPa	ISO 527
^[C] Stress at break	190 / 110	MPa	ISO 527
^[C] Strain at break	3.5 / 6.5	%	ISO 527
^[C] Charpy impact strength, +23°C	85 / 95	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	70 / 70	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	12 / 20	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	9 / 9	kJ/m ²	ISO 179/1eA
^[C] Shore D hardness	83 / *	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	200 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 8.00 MPa	135 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	30 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	110 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E12 / 1E10	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E12	Ohm	IEC 62631-3-2
^[C] Electric strength	34 / 31	kV/mm	IEC 60243-1
^[C] Comparative tracking index	- / 550	-	IEC 60112

[C]: CAMPUS

Grilon BG-30 natural

PA6-GF30

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	7 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2 / *	%	Sim. to ISO 62
^[C] Density	1350 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	260	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	300	mm/s	ISO 294
Injection Molding, pressure at hold	75	MPa	ISO 294

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Granules, Natural Color

Special Characteristics

Heat stabilized or stable to heat

Applications

Automotive, Electrical and Electronical, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa