

**Product Texts**

LNP THERMOCOMP PF006 compound is based on Nylon 6 resin containing 30% glass fiber.

UL Yellow Card Link [E121562-101281583](https://www.ul.com/yellowcard/E121562-101281583)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.35	mm/mm	ASTM D 955
Mold Shrinkage, TD	1.1	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	8580	MPa	ISO 527
Stress at break	128	MPa	ISO 527
Strain at break	2.9	%	ISO 527
Flexural modulus	8100	MPa	ISO 178
Flexural strength	203	MPa	ISO 178
Izod impact strength, +23°C, 4mm	55	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	8	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Modulus	8750	MPa	ASTM D 638
Tensile Strength at Break	129	MPa	ASTM D 638
Elongation at Break	2.8	%	ASTM D 638
Flexural Modulus	6960	MPa	ASTM D 790
Flexural Strength	201	MPa	ASTM D 790
Izod Impact notched, 1/8 in	117	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	827	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	203	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
<b>ASTM Data</b>			
DTUL @ 66 psi	219	°C	ASTM D 648
DTUL @ 264 psi	206	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Humidity absorption	1.53	%	Sim. to ISO 62
Density	1370	kg/m <sup>3</sup>	ISO 1183
Water Absorption, 24hr	0.86	%	ASTM D 570
Density	1370	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	265 - 275	°C	-
Mold temperature	80 - 95	°C	-
Zone 1	250 - 260	°C	-
Zone 2	265 - 275	°C	-
Zone 3	275 - 290	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.3 - 0.7	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Regional Availability**

North America