

Staramide PF00AES

(PA66+PA6)-GF

Eurostar Engineering Plastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	16000	MPa	ISO 527
Stress at break	210	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus, 23°C	15000	MPa	ISO 178
Izod impact strength, +23°C	55	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	13	kJ/m ²	ISO 180/1A
Izod notched impact strength Temperature	11	kJ/m ²	ISO 180/1A
	-40	°C	-
Rockwell hardness	L 114	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	235	°C	ISO 75-1/-2
Vicat softening temperature, A	240	°C	ISO 306
Vicat softening temperature, B	230	°C	ISO 306
Coeff. of linear therm. expansion, parallel	12	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	136	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.75	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
Dissipation factor, 1MHz	150	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	19	kV/mm	IEC 60243-1
Comparative tracking index	500	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	2.75	%	Sim. to ISO 62
Humidity absorption	0.85	%	Sim. to ISO 62
Density	1580	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe