

NEVIMID 6 K G30L

PA6-GF30

Nevicolor S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	9500	MPa	ISO 527
Stress at break	160	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	8000	MPa	ISO 178
Izod impact strength, +23°C	70	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	13	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	210	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2
Vicat softening temperature, A	215	°C	ISO 306
Vicat softening temperature, B	205	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
Other properties			
Value			
Humidity absorption	2	%	Sim. to ISO 62
Density	1350	kg/m ³	ISO 1183

Characteristics**Regional Availability**

Europe