

**NGF30-01NC**

PA6-GF30

Next Polymers Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.006	mm/mm	ASTM D 955
Mechanical properties	dry / cond	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	130 / 90	MPa	ASTM D 638
Elongation at Break	4 / 6	%	ASTM D 638
Flexural Modulus	6800 / 5300	MPa	ASTM D 790
Flexural Strength	175 / 160	MPa	ASTM D 790
Rockwell Hardness	R 125 /	-	ASTM D 785
Izod Impact notched, 1/8 in	88.3 / 108	J/m	ASTM D 256
Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.8	mm	-
DTUL @ 66 psi	200	°C	ASTM D 648
DTUL @ 264 psi	150	°C	ASTM D 648
Melting Temperature	220	°C	ASTM D 3418
Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	>1E13 / -	Ohm*m	IEC 62631-3-1
Electric strength	26 / 24	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	-	IEC 60112
Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	1.7	%	ASTM D 570
Water Absorption, Equilibrium	5.2	%	ASTM D 570
Density	1470	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Delivery form**

Natural Color

**Special Characteristics**

Flame retardant

**Applications**

Electrical and Electronical, Encapsulation

**Regional Availability**

Asia Pacific