

**POLIMID B 30 GF V0HFR KW**

PA6-GF30

Poliblend S.p.a.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	<b>0.6</b>	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>7500</b>	MPa	ISO 527
Yield strain	<b>2.5</b>	%	ISO 527
Stress at break	<b>120</b>	MPa	ISO 527
Strain at break	<b>2.5</b>	%	ISO 527
Izod impact strength, +23°C	<b>50</b>	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>222</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>175</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>205</b>	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	<b>V-2</b>	class	IEC 60695-11-10
Burning behav. at thickness h Thickness tested	<b>V-2</b>	class	IEC 60695-11-10
	<b>0.8</b>	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	<b>1E12</b>	Ohm*m	IEC 62631-3-1
Comparative tracking index	<b>550</b>	-	IEC 60112
<b>Other properties</b>			
Density	<b>1390</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

Flame retardant, Halogen-free, Phosphorus-free, Heat stabilized or stable to heat

**Regional Availability**

Europe