

Product Texts

PA6 30% glass fibre reinforced injection moulding grade. Natural colour.

Suitable for parts requiring high stiffness and good mechanical resistance.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9300 / 6400	MPa	ISO 527
^[C] Stress at break	180 / 105	MPa	ISO 527
^[C] Strain at break	3.9 / 4.8	%	ISO 527
^[C] Charpy impact strength, +23°C	95 / 110	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	70 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	13 / 20	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	11 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	200 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	215 / *	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	210 / *	°C	ISO 306
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Yellow Card available	yes / *	-	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / 1E11	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
^[C] Comparative tracking index	600 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	7.5 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2 / *	%	Sim. to ISO 62
^[C] Density	1350 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-
Melt temperature	240 - 280	°C	-
Mold temperature	80 - 90	°C	-

Characteristics

Processing

Injection Molding

Additives

Release agent

Delivery form

Granules, Natural Color

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature

240 - 280°C

Mold Temperature

80 - 90°C

Injection Speed

medium-high