

Product Texts

Partially recycled PA6 30% glass-fibre-reinforced injection moulding grade. Heat stabilized. Black colour.

The recycled material has been developed to reduce its environmental impact in comparison to traditional virgin options. Suitable for parts requiring high stiffness and good mechanical resistance.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	50 / *	cm ³ /10min	ISO 1133
Temperature	275 / *	°C	-
Load	5 / *	kg	-
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9400 / -	MPa	ISO 527
^[C] Stress at break	150 / -	MPa	ISO 527
^[C] Strain at break	3 / -	%	ISO 527
^[C] Charpy impact strength, +23°C	61 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	8 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	219 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	200 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	215 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1370 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Granules, Black

Certifications

Recycled Resin Content

Additives

Release agent

Regional Availability

Europe

Other text information

Injection molding

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 °C, dew point -20 °C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature
240 - 280°C

Mold Temperature
80 - 90°C

Injection Speed
medium-high