

SCANAMID 6 B12^ F30 AS

PA6-GF30

Polykemi AB

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Strength	- / 127	MPa	ISO 527
Yield strain	- / 9.5	%	ISO 527
Strain at break	- / 10	%	ISO 527
Flexural modulus, 23°C	- / 7100	MPa	ISO 178
Charpy impact strength, +23°C	- / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	14 / 16	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	198 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	213 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Glow Wire Ignition Temperature (GWIT)	650	°C	IEC 60695-2-13
GWIT - thickness tested (1)	2	mm	-
Other properties			
Density	1370 / -	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe, Asia Pacific

Delivery form

Granules