

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9500 / 6200	MPa	ISO 527
^[C] Stress at break	160 / 95	MPa	ISO 527
^[C] Strain at break	2.5 / 6.7	%	ISO 527
^[C] Charpy impact strength, +23°C	55 / 70	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	48 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	9 / 15	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	7 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	202 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	218 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1350 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Viscosity number	139 / *	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Regional Availability

Europe