

Taromid B 280 Z2 G6

PA6-GF30

Taro Plast S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	5	g/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	7700	MPa	ISO 527
Stress at break	135	MPa	ISO 527
Strain at break	6	%	ISO 527
Flexural modulus, 23°C	7200	MPa	ISO 178
ASTM Data			
Izod Impact notched, 1/8 in	210	J/m	ASTM D 256
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	222	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	202	°C	ISO 75-1/-2
Vicat softening temperature, B	212	°C	ISO 306
Coeff. of linear therm. expansion, parallel	30	E-6/K	ISO 11359-1/-2
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.6	mm	-
Limiting Oxygen Index	23	%	ASTM D 2863
Electrical properties			
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Comparative tracking index	550	-	IEC 60112
Other properties			
Water absorption	5.5	%	Sim. to ISO 62
Density	1310	kg/m ³	ISO 1183

Characteristics**Additives**

Release agent

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Features

Low Odor

Applications

Automotive, Electrical and Electronical

Regional Availability

Europe