

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.1 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	8200 / 5400	MPa	ISO 527
^[C] Stress at break	140 / 90	MPa	ISO 527
^[C] Strain at break	4 / 6	%	ISO 527
Flexural modulus, 23°C	8000 / 5200	MPa	ISO 178
^[C] Charpy impact strength, +23°C	86 / 100	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	85 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	18 / 30	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	11 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	200 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Yellow Card available	yes / *	-	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E12	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1320 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing
Injection Molding

Special Characteristics
High impact or impact modified

Delivery form
Natural Color

Applications
Sports Equipment