

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>7400 / -</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>90 / -</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>2 / -</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>35 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>220 / *</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>190 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>215 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	<b>V-2 / *</b>	class	IEC 60695-11-10
Yellow Card available	<b>yes / *</b>	-	-
<sup>[C]</sup> Burning Behav. at thickness h	<b>V-2 / *</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / *</b>	mm	-

[C]: CAMPUS

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Comparative tracking index	<b>500 / -</b>	-	IEC 60112

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1380 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Features**

Laser Markable

**Special Characteristics**

Flame retardant, Halogen-free

**Applications**

Electrical and Electronical