

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	11000 / 7000	MPa	ISO 527
<sup>[C]</sup> Stress at break	140 / 95	MPa	ISO 527
<sup>[C]</sup> Strain at break	2.5 / 3.5	%	ISO 527
Flexural modulus, 23°C	10000 / 6500	MPa	ISO 178
Flexural strength	210 / 140	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	50 / 55	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	45 / 45	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	8 / 11	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	7 / 8	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	205 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	215 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	210 / *	°C	ISO 306
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning Behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	>1E13 / -	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	* / 1E14	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	31 / -	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	600 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Density	1420 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Viscosity number	145 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Black

**Special Characteristics**

Flame retardant, Halogen-free, Phosphorus-free, Heat stabilized or stable to heat