

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	10400 / -	MPa	ISO 527
^[C] Stress at break	160 / -	MPa	ISO 527
^[C] Strain at break	2.1 / -	%	ISO 527
^[C] Charpy impact strength, +23°C	45 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	8.1 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Delivery form

Black

Applications

Automotive