

TEKUMID B H9 GF6

PA6-GF30

Tekuma Kunststoff GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	54	g/10min	ISO 1133
Temperature	275	°C	-
Load	5	kg	-
Mechanical properties			
	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	8700 / 7600	MPa	ISO 527
Tensile Strength	155 / 130	MPa	ISO 527
Flexural strength	220 / 180	MPa	ISO 178
Charpy impact strength, +23°C	60 / 58	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	52 / 53	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	11 / 13	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	9 / 10	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	200 / *	°C	ISO 75-1/-2
Vicat softening temperature, B	200 / *	°C	ISO 306
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Electrical properties			
	dry / cond	Unit	Test Standard
ISO Data			
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2
Other properties			
	dry / cond	Unit	Test Standard
Water absorption	1.8 / *	%	Sim. to ISO 62
Density	1360 / -	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	>2	h	-
Processing humidity	≤0.15	%	-
Melt temperature	260 - 290	°C	-
Mold temperature	60 - 100	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Special Characteristics

Heat stabilized or stable to heat