

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>5564</b>	MPa	ASTM D 638
Tensile Strength	<b>79.3</b>	MPa	ASTM D 638
Elongation at Break	<b>4</b>	%	ASTM D 638
Flexural Modulus	<b>4757</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>67.3</b>	J/m	ASTM D 256

  

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Glass Transition Temperature	<b>222</b>	°C	ASTM E 1356

  

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1400</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Black

**Additives**

Lubricants

**Special Characteristics**

Heat stabilized or stable to heat

**Applications**

Automotive

**Regional Availability**

North America