

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.8	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	11500	MPa	ISO 527
^[C] Stress at break	190	MPa	ISO 527
^[C] Strain at break	3.3	%	ISO 527

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1380	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form

Black

Special Characteristics

U.V. stabilized or stable to weather