

CP PRYME® Nylon 6 N133L NAT

PA6-GF33

Chase Plastics

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	165	MPa	ASTM D 638
Elongation at Break	2	%	ASTM D 638
Flexural Modulus	10300	MPa	ASTM D 790
Izod Impact notched, 1/8 in	96	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	213	°C	ASTM D 648
DTUL @ 264 psi	204	°C	ASTM D 648
Melting Temperature	218	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1390	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets, Natural Color

Regional Availability

North America