

Fiberfil® FPI-33 BK

PA6-GF33

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	150	MPa	ASTM D 638
Flexural Strength	232	MPa	ASTM D 790
Izod Impact notched, 1/8 in	130	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	207	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1380	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets, Black

Regional Availability

North America