

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	10800 / 7300	MPa	ISO 527
Stress at break	190 / 125	MPa	ISO 527
Strain at break	3.5 / 5.5	%	ISO 527
Flexural strength	280 / 210	MPa	ISO 178
Charpy impact strength, +23°C	95 / 110	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	90 / 100	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	17 / 26	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	15 / 24	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	16 / 21	kJ/m ²	ISO 180/1A
Izod notched impact strength Temperature	12 / 16	kJ/m ²	ISO 180/1A
	-30	°C	-

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	215 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	17 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	64 / *	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Yellow Card available	yes / *	-	-

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3.9 / 6.4	-	IEC 62631-2-1
Dissipation factor, 1MHz	210 / 1900	E-4	IEC 62631-2-1
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
Comparative tracking index	500 / -	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	6.2 / *	%	Sim. to ISO 62
Humidity absorption	2 / *	%	Sim. to ISO 62
Density	1410 / -	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-
Melt temperature	270 - 300	°C	-
Mold temperature	80 - 90	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa