

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	9700 / -	MPa	ISO 527
<sup>[C]</sup> Stress at break	160 / -	MPa	ISO 527
<sup>[C]</sup> Strain at break	3.6 / -	%	ISO 527
Flexural modulus, 23°C	8600 / -	MPa	ISO 178
Flexural strength	243 / -	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	86 / -	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	15 / -	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Yellow Card available	yes / *	-	-

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Density	1410 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding

### Special Characteristics

High impact or impact modified

### Delivery form

Black