

Product Texts

Vydyne B 35 GF NT is standard flow, 35% glass-fiber reinforced PA6 resin. Available in natural, this product is also lubricated for improved machine feed and flow.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	11000 / -	MPa	ISO 527
^[C] Stress at break	193 / -	MPa	ISO 527
^[C] Strain at break	2.9 / -	%	ISO 527
^[C] Charpy impact strength, +23°C	95 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	85 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	18 / -	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	13 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	210 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	215 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	18 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	65 / *	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Electric strength	25 / -	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	1 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2 / *	%	Sim. to ISO 62
^[C] Density	1410 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Additives

Lubricants

Delivery form

Pellets, Natural Color

Regional Availability

North America, Europe, Asia Pacific