

## Product Texts

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

**Zytel® 73G35HSL BK262 is a 35% glass fiber reinforced, heat stabilized, black polyamide 6 resin for injection molding.**

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.1 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	11000 / 6500	MPa	ISO 527
<sup>[C]</sup> Stress at break	190 / 120	MPa	ISO 527
<sup>[C]</sup> Strain at break	3.2 / 6	%	ISO 527
<sup>[C]</sup> Tensile creep modulus, 1h	* / 6000	MPa	ISO 899-1
<sup>[C]</sup> Tensile creep modulus, 1000h	* / 5000	MPa	ISO 899-1
<sup>[C]</sup> Charpy impact strength, +23°C	85 / 90	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	80 / 90	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	14 / 22	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	10 / 10	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Puncture energy, +23°C	3 / 6	J	ISO 6603-2

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	55 / *	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	208 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	220 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	215 / *	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	18 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	102 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning rate, FMVSS, Thickness 1 mm	24	mm/min	ISO 3795 (FMVSS 302)

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Water absorption	5.8 / *	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	2.1 / *	%	Sim. to ISO 62
<sup>[C]</sup> Density	1410 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			

[C] Viscosity number **143 / \*** cm<sup>3</sup>/g ISO 307, 1157, 1628  
[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets, Black

**Additives**

Lubricants, Release agent

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America