

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577
Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	123	MPa	ISO 527
Flexural modulus, 23°C	9480	MPa	ISO 178
Flexural strength	209	MPa	ISO 178
Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	230	°C	ISO 75-1/-2
Other properties	Value	Unit	Test Standard
Density	1410	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Special Characteristics

High impact or impact modified

#### Applications

Automotive

#### Certifications

Recycled Resin Content

#### Regional Availability

North America