

Staramide BG8

PA6-GF40

Eurostar Engineering Plastics

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Thermal conductivity of melt	0.33	W/(m K)	-
Mechanical properties			
ISO Data			
Tensile Modulus	13500	MPa	ISO 527
Stress at break	195	MPa	ISO 527
Strain at break	2	%	ISO 527
Charpy impact strength, +23°C	150	kJ/m ²	ISO 179/1eU
Izod notched impact strength, +23°C	17	kJ/m ²	ISO 180/1A
Izod notched impact strength	15	kJ/m ²	ISO 180/1A
Temperature	-40	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	212	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	224	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	17	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	82	E-6/K	ISO 11359-1/-2
Oxygen index	25	%	ISO 4589-1/-2
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.75	mm	-
Electrical properties			
ISO Data			
Relative permittivity, 1MHz	3.4	-	IEC 62631-2-1
Dissipation factor, 1MHz	160	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	20	kV/mm	IEC 60243-1
Comparative tracking index	500	-	IEC 60112
Other properties			
Density	1470	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding, Other Extrusion

Features

Low Odor

Delivery form

Pellets

Regional Availability

Europe