

Product Texts

Polyamide 6, 40% glass fiber reinforced, improved flowability, for injection moulding, natural color

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	45 / *	cm ³ /10min	ISO 1133
Load	5 / *	kg	-
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	12000 / -	MPa	ISO 527
^[C] Stress at break	200 / -	MPa	ISO 527
^[C] Strain at break	3 / -	%	ISO 527
Flexural modulus, 23°C	10000 / -	MPa	ISO 178
^[C] Charpy impact strength, +23°C	100 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	15 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	210 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	215 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1450 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	125 / *	cm ³ /g	ISO 307, 1157, 1628

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color