

| Mechanical properties | Value | Unit | Test Standard |
|--|--------------|-------------------|----------------------|
| ISO Data | | | |
| ^[C] Tensile Modulus | 13500 | MPa | ISO 527 |
| ^[C] Stress at break | 215 | MPa | ISO 527 |
| ^[C] Strain at break | 3.1 | % | ISO 527 |
| ^[C] Charpy impact strength, +23°C | 18 | kJ/m ² | ISO 179/1eU |

[C]: CAMPUS

| Thermal properties | Value | Unit | Test Standard |
|---|--------------|-------------|----------------------|
| ISO Data | | | |
| ^[C] Temp. of deflection under load, 1.80 MPa | 213 | °C | ISO 75-1/-2 |
| ^[C] Temp. of deflection under load, 0.45 MPa | 218 | °C | ISO 75-1/-2 |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| ^[C] Density | 1470 | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics

Delivery form

Natural Color