

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	172	MPa	ASTM D 638
Elongation at Break	2.5	%	ASTM D 638
Flexural Modulus	11030	MPa	ASTM D 790
Flexural Strength	255	MPa	ASTM D 790
Izod Impact notched, 1/8 in	128	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	220	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1480	kg/m ³	ASTM D 792

Characteristics

Delivery form

Black

Regional Availability

Europe, Asia Pacific

Certifications

RoHS compliant