

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>5</b>	g/10min	ASTM D 1238
Temperature	<b>250</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	<b>162</b>	MPa	ASTM D 638
Elongation at Break	<b>6</b>	%	ASTM D 638
Flexural Modulus	<b>10790</b>	MPa	ASTM D 790
Flexural Strength	<b>265</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>147</b>	J/m	ASTM D 256
<b>Other properties</b>			
Density	<b>1510</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Injection Molding

**Chemical Resistance**

General Chemical Resistance

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

Europe, Asia Pacific