

Product Texts

LNP KONDUIT PX10323 compound is based on Nylon 6 resin containing glass fiber. Added features of this grade include: Thermally Conductive.

UL Yellow Card Link [E45329-104457424](https://www.ul.com/yellow-card-link/E45329-104457424)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.2	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.22	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	14000	MPa	ISO 527
Stress at break	73	MPa	ISO 527
Strain at break	0.8	%	ISO 527
Flexural modulus	14300	MPa	ISO 178
Izod impact strength, +23°C, 4mm	6	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	3	kJ/m ²	ISO 180/1A

ASTM Data			
Tensile Modulus	13700	MPa	ASTM D 638
Tensile Strength at Break	70	MPa	ASTM D 638
Elongation at Break	0.9	%	ASTM D 638
Flexural Modulus	14200	MPa	ASTM D 790
Izod Impact notched, 1/8 in	30	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	73	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	201	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (GWIT)	825	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1	mm	-
Glow Wire Ignition Temperature (GWIT)	960	°C	IEC 60695-2-13
GWIT - thickness tested (3)	3	mm	-
ASTM Data			
DTUL @ 264 psi	186	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1.05E6	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1610	kg/m ³	ISO 1183
Density	1610	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	270 - 300	°C	-
Mold temperature	80 - 100	°C	-
Zone 1	260 - 290	°C	-
Zone 2	270 - 300	°C	-
Zone 3	270 - 300	°C	-
Screw speed	30 - 150	rpm	-

Back pressure	≥-3	MPa	-
---------------	-----	-----	---

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Special Characteristics

Thermally Conductive