

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>6200</b>	MPa	ISO 527
Stress at break	<b>95</b>	MPa	ISO 527
Strain at break	<b>3.2</b>	%	ISO 527
Flexural modulus, 23°C	<b>6200</b>	MPa	ISO 178
Izod impact strength, +23°C	<b>45</b>	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	<b>5</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>185</b>	°C	ISO 75-1/-2
<b>Electrical properties</b>			
<b>ISO Data</b>			
Comparative tracking index	<b>400</b>	-	IEC 60112
<b>Other properties</b>			
Density	<b>1330</b>	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Injection Molding, Other Extrusion

#### Delivery form

Pellets

#### Special Characteristics

Flame retardant

#### Features

Low Odor

#### Regional Availability

Europe