

DOMAMID 6G8LS3UV1 500

PA6-GF8

DOMO Engineering Plastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3500	MPa	ISO 527
Stress at break	60	MPa	ISO 527
Strain at break	25	%	ISO 527
Flexural modulus, 23°C	3100	MPa	ISO 178
Charpy impact strength, +23°C	65	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6.5	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	55	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	221	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	190	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	215	°C	ISO 75-1/-2
Vicat softening temperature, B	210	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1280	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	240 - 260	°C	-
Mold temperature	80 - 90	°C	-

Characteristics**Processing**

Injection Molding

Features

Laser Markable

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Regional Availability

North America, Europe, Asia Pacific