

Product Texts

Injection Molding, 50% Glass Reinforced, Heat Stabilized

ISO 1043 PA6-GF50

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	16800 / 10200	MPa	ISO 527
^[C] Stress at break	225 / 140	MPa	ISO 527
^[C] Strain at break	3 / 5	%	ISO 527
^[C] Charpy impact strength, +23°C	100 / 110	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	90 / 90	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	20 / 25	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	15 / 15	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	205 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	215 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	70 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
^[C] Burning rate, FMVSS, Thickness 1 mm	43.3	mm/min	ISO 3795 (FMVSS 302)

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	5 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1.5 / *	%	Sim. to ISO 62
^[C] Density	1570 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Viscosity number	140 / *	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Processing humidity	≤0.12	%	-
Melt temperature	270 - 290	°C	-
Mold temperature	80 - 120	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Additives

Release agent

Other text information

Injection molding

PREPROCESSING

Residual moisture content: 0.03 - 0.12%

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

PROCESSING

Melt temperature (Tmin - Tmax): 270 - 290 °C

Mold temperature: 80 - 120 °C