

PlusTek PB209G50BK11

PA6-GF50

Polyram

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.1 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5 / *	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	17700 / 10400	MPa	ISO 527
Tensile Strength	220 / 140	MPa	ISO 527
Strain at break	3.1 / 4.8	%	ISO 527
Izod notched impact strength, +23°C	20 / -	kJ/m ²	ISO 180/1A

Other properties	dry / cond	Unit	Test Standard
Water absorption	5 / *	%	Sim. to ISO 62
Humidity absorption	1.5 / *	%	Sim. to ISO 62
Density	1550 / -	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	2 - 3	h	-
Processing humidity	≤0.15	%	-
Mold temperature	90 - 95	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	290 - 300	°C	-
Zone 2	290 - 300	°C	-
Zone 3	290 - 300	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Certifications

RoHS compliant

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa