

**Tarnamid® T-27 GF150**

PA6-GF50

Grupa Azoty S.A.

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>10 / *</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>275 / *</b>	°C	-
Load	<b>5 / *</b>	kg	-
Molding shrinkage, parallel	<b>0.4 / *</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>1.0 / *</b>	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>15500 / -</b>	MPa	ISO 527
Tensile Strength	<b>195 / -</b>	MPa	ISO 527
Strain at break	<b>3.5 / -</b>	%	ISO 527
Flexural modulus, 23°C	<b>13000 / -</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>90 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>17 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	<b>18 / -</b>	kJ/m <sup>2</sup>	ISO 180/1A
Ball indentation hardness	<b>280 / -</b>	MPa	ISO 2039-1
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>221 / *</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>210 / *</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>215 / *</b>	°C	ISO 306
Burning behav. at thickness h	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>3.2 / *</b>	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Relative permittivity, 1MHz	<b>3.7 / 4.7</b>	-	IEC 62631-2-1
Dissipation factor, 1MHz	<b>160 / 1300</b>	E-4	IEC 62631-2-1
Volume resistivity	<b>1E13 / 1E10</b>	Ohm*m	IEC 62631-3-1
Surface resistivity	<b>* / 1E11</b>	Ohm	IEC 62631-3-2
Electric strength	<b>31 / 27</b>	kV/mm	IEC 60243-1
Comparative tracking index	<b>525 / 525</b>	-	IEC 60112
<b>Other properties</b>			
Water absorption	<b>5 / *</b>	%	Sim. to ISO 62
Humidity absorption	<b>1.5 / *</b>	%	Sim. to ISO 62
Density	<b>1550 / -</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Delivery form**

Granules, Black, Natural Color

**Applications**

Automotive, Building Construction, Electrical and Electronical

**Regional Availability**

Europe