

**TRIMID® N60G50HL BK**

PA6-GF50

Amco Polymers

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Stress at break	181 / 118	MPa	ISO 527
Strain at break	1.5 / 4	%	ISO 527
Flexural modulus, 23°C	13500 / 8340	MPa	ISO 178
Flexural strength	327 / 202	MPa	ISO 178
Charpy notched impact strength, +23°C	14.1 / 25.2	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	14.1 / 25.2	kJ/m <sup>2</sup>	ISO 180/1A

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	227 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	233 / *	°C	ISO 75-1/-2

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Density	1570 / -	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	71.1	°C	-
Pre-drying - Time	4	h	-
Melt temperature	271 - 293	°C	-
Mold temperature	26.7 - 93.3	°C	-
Zone 1	254	°C	-
Zone 2	268	°C	-
Zone 3	285	°C	-
Screw speed	30 - 60	rpm	-
Injection pressure	68.9	MPa	-
Back pressure	0.0689 - 0.689	MPa	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets, Black

**Additives**

Lubricants

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa