

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Thermal conductivity of melt	0.33	W/(m K)	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	10500	MPa	ISO 527
Tensile Strength	145	MPa	ISO 527
Flexural modulus, 23°C	9000	MPa	ISO 178
Charpy impact strength, -30°C	30	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	6	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	240	°C	ISO 75-1/-2
Vicat softening temperature, A	250	°C	ISO 306
Coeff. of linear therm. expansion, parallel	30	E-6/K	ISO 11359-1/-2

Electrical properties	Value	Unit	Test Standard
ISO Data			
Surface resistivity	100000	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1340	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75	°C	-
Pre-drying - Time	6 - 16	h	-
Processing humidity	≤0.1	%	-
Melt temperature	290	°C	-
Mold temperature	90 - 120	°C	-
Zone 1	290 - 310	°C	-
Zone 2	290 - 310	°C	-
Zone 3	290 - 310	°C	-
Nozzle temperature	280 - 300	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Black

Additives

Lubricants

Special Characteristics

Increased electrical conductivity

Features

Tribologic Grade

Applications

Automotive, IT / Business Machine, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific